



AMERICAN BILTRITE

AB-260

60 DURO NEOPRENE BLEND / COMMERCIAL GRADE / SATIN FINISH / BLACK /
MODERATE OIL RESISTANT / UNTRIMMED / NO POWDER

GAUGE	ITEM NUMBER 36"	ITEM NUMBER 48"
SPECIFICATION: BC606		
1/16"	266-04-362 (S)	266-04-482 (S)
3/32"	266-06-362 (S)	266-06-482 (S)
1/8"	266-08-362 (S)	266-08-482 (S)
3/16"	266-12-362 (S)	266-12-482 (S)
*1/4"	266-16-36S (S)	266-16-48S (S)

* Plate Finish (Powdered / Trimmed)
(S) Normally available from inventory.

STANDARD DIMENSIONS

GAUGE	TOLERANCE (+/-)	ROLL LENGTH		APPROX. WEIGHT PER ROLL		APPROX. SQ. FT. PER ROLL	
		36"	48"	36"	48"	36"	48"
1/16"	.016	150'	150'	216 LBS.	288 LBS.	450 SQ. FT.	600 SQ. FT.
3/32"	.016	50'	50'	110 LBS.	146 LBS.	150 SQ. FT.	200 SQ. FT.
1/8"	.020	50'	50'	146 LBS.	194 LBS.	150 SQ. FT.	200 SQ. FT.
3/16"	.031	50'	50'	219 LBS.	292 LBS.	150 SQ. FT.	200 SQ. FT.
1/4"	.031	50'	50'	291 LBS.	388 LBS.	150 SQ. FT.	200 SQ. FT.

Maximum pieces per roll: 2
Minimum piece length: 10'
Width tolerance: +1"/-1/2"
Length tolerance: +/-10%

Minimum Order:
Inventory Item: 1 Roll
Non-inventory Item: 2,000 lbs.
Custom Made Item: 3,000 lbs.

AB-260 PHYSICAL PROPERTIES (Excluding 1/4")

DESCRIPTION	TYPICAL VALUE	UNITS
POLYMER	CR/SBR/NBR	
HARDNESS	60	SHORE "A" DUROMETER
TENSILE	830	PSI
ELONGATION	520	%
OIL AGING # 1 OIL	70 HOURS	100 ° C
CHANGED-HARDNESS	1	POINTS
CHANGED-TENSILE	3	%
CHANGED-ELONGATION	-47	%
CHANGED-MASS	-2	%
CHANGED-VOLUME	0	%